

Technical Data Sheet



V57DB-Samand Bum

Nirumand Polymer

Nirumand Polymer Co.
Filled & Reinforced Engineering Plastics

Product Description

V57DB-Samand Bum is copolymer polypropylene toughened with EPDM and filled with mineral fillers by high impact strength. This compound is used in automotive applications especially bumper parts and other utility products. This grade is designed to be processed in conventional injection molding techniques.

Physical Properties	Value	Unit	Test Method
Density	0.9	gr/cm ³	ISO 1183
Melt Mass-flow Rate (MFR) (230°C/2.16 kg)	10±2	gr/10 min	ASTM D1238
Filler Content	≤ 3	%	ISO 3451
Shrinkage	1.6-1.8	%	ASTM D955
Mechanical Properties	Value	Unit	Test Method
Tensile Strength @ Yield	≥17	MPa	ISO 527
Tensile Strength @ Break	≥14	MPa	ISO 527
Elongation @ Break	≥100	%	ISO 527
Flexural Modulus	950±50	MPa	ASTM D790
Impact	Value	Unit	Test Method
Notched Izod Impact (23°C)	≥30	KJ/m ²	ISO 180
Hardness	Value	Unit	Test Method
Durometer Hardness (after 5 S)	57±3	Shore D	ISO 868

◆ Values shown are average & are not to be considered as product specifications.

Web-site: www.npolymer.com

Address: Abbas abad Industrial Zone-Tehran-Iran

E-mail: Sales@npolymer.com

Tel: (+9821)36425177 Fax: (+9821)36425178